

Technical Data - Renia Gummilösung

Rubber solution based on natural rubber, tailored to work on shoes. Umbugg cement for all sewing work on shoes, belts, handbags, leather clothing, uppers. The adhesive film remains very elastic.

Technical data

Color:	bright yellow	Viscosity [mPa.s]:	2500	Density [g/l]:	880
pH-Value:	n.a.	Solid Content [%]	13	Drying time [min]:	5
Pressure [bar]:	1 - 5	Reactivation temperature [°C]:	n.a.	Open time [min]:	20
Temp.resistance [°C]:	60	peel strength* [N/mm]:	4	React.time [s]:	n.a.

*determined with test rubber on test rubber, with a drying time of 15 minutes, after the adhesive has fully cured. Value varies with different material combinations, own tests are necessary.

Application

After applying the glue, the parts can be assembled within 5 to 20 minutes and sewn immediately. The needle does not stick and the thread channel does not close. The glued parts can be removed and rejoined several times for correction.

Thinning/Cleaning

The adhesive can be thinned with Renia DeSohl or Renia Thinner. Renia thinner or acetone can also be used to clean adhesive containers and application devices.

Storage and Transportation

Minimum shelf life of 12 months at 20°C.

Hazard designation

according to CLP, see MSDS

Packages

Article-Nr.	Package	Net-Contents	Units per Box
180200	250 ml - Can	200 g	69
180258	580 g - Can	0,58 kg	24
180404	5 l - Can	3,5 kg	6
180410	12 l - Can	8,5 kg	2

Please note: This product data sheet only provides general information. The properties and characteristics listed above are approximations and do not constitute product specifications. Due to the many conditions of application and processing that are outside of our influence and responsibility, as well as the multitude of different materials, we recommend to always conduct specific tests on the materials and under the conditions in question. Therefore, no liability can be accepted for results derived from specifications and information outlined in this data sheet. In line with our conditions of sale, we only guarantee the consistent technical properties of our high-quality products. This technical data sheet invalides and replaces all prior versions.